Marshall-Tufflex Ltd



55-65 Castleham Road, St Leonards on Sea

East Sussex, TN38 9NU

Customer Services: +44 (0) 1424 856600

T: +44 (0) 1424 856655

E: sales@marshall-tufflex.com www.marshall-tufflex.com

GRP Ladder and Tray Support Systems Product Data Sheet

Product Range	GRP Support Systems	Image
Description	Ladder and Tray Support Systems	
Key Features	For wall mounting and ceiling mounting applications. Brackets for Pultruded Ladder and Pressed Tray Optional Fixing rail for Pultruded Ladder Optional M10 x 30mm Clamp bolts for use with Fixing Rail	
	Load at mid-point of brackets (L/2) 1.25KN (only valid if the main supporting part is sufficiently and correctly fixed).	
Dimensions	L (Protruded) = width of Ladder plus 10mm	
	L (Pressed) = Width of Cable Tray plus 20mm	
Material(s)	GRP - Glass-Fibre Reinforced Polyester (Halogen free).	
	Clamp bolts – Stainless Steel	3
Compliance / Standards(s)	CE & UKCA Marked	3
	Low Voltage Directive 2014/35/EU	
	The Electrical Equipment (Safety) Regulations 2016	
	BS 7671:2018	
	Refer to sheet 2 for complete list	
Packaging	Recyclable	



Sustainability


We work hard to ensure our products meet the highest standards and are totally committed to the environment and maximising our usage of recycled material within our manufacturing process.

Our PVC-U products are manufactured from an average of 80% recycled plastic, with some extruded products produced from 100% recycled material.



(eama





Properties	Standards references & Standards Designations	PRESS type resin R96	PULTRUSION type resin R6204	Units
Fire Behaviour		_		<u> </u>
Inflammability	IEC 695-2-1 Glow Wire test	960	960	°C
Inflammability	UL 94 Test for flammability of plastic materials	V0	V0	-
Flammability	NF P 92-507 Fire Behaviour of Building Materials	М3	M2	-
Spread of Flame	ASTM E84 Surface burning characteristics of building materials	35	35	Index FSI
Spread of Flame	BS 476 Part 7 Surface spread of flame test for materials	Class 2	Class 2	-
Fire Propagation	BS 476 Part 6 Fire Propagation test for materials	18,3	14,1	Index
Oxygen & Smoke Index	NF F 16-101 Fire Behaviour of materials for rolling stock	I2 (>32) F0 (<5;	I2 (>32) F0 (<20;	-
Smoke	BS 6853 App 52 Fire Precautions in the design and construction of rolling stock	10,47 / 11,23	17,34 / 18,74	Index
Oxygen Index	ASTM D 2863	> 35	-	%
Fire Protection Index	EMPA	5.3	5.3	Index
Fire Standard	DIN 4102	B2	B2	-
Fire Standard	IEC 332-3 Fire Resistance of Cable	Passed		
Mechanical Behaviour		•	•	
Breaking Point	NEMA FG1 Fibre glass cable ladder systems	N/A	A to C Class	-
Tensile Strength at Break Point	DIN 53455 / ISO 527	37	155	MPa
Modulus of Elasticity	DIN 53457 / ISO 527-4	5000< <7000	10000< <15000	MPa
Choc Resistance	DIN 53453	27 / IPxx7	80 / 25	kJ/m m²
Heat Resistance	VSM 77116 Martens Point	-90	-200 / 80	°C
Accelerated Aging	ISO 4892-2 Mechanical UV Resistance	Excellent	Excellent	-
Degrees of Protection	NF EN 50102 Degrees of Protection against mechanical impact	IK10	IK09 – IK10	-
Electrical Behaviour				
Surface Resistivity	DIN 53482 / EN 50014	~1012	~10¹¹	Ω
Volume Resistivity	DIN 53482	~10¹³	~1012	Ωm
Breakage Voltage	IEC 243-1	> 15	> 15	kV/m m

DOC02285 Issue 3 Page 2 of



